

ALPHA[®] TELECORE[™] XL-825

NO-CLEAN, WIRE SOLDER

DESCRIPTION

ALPHA Telecore XL-825 is a cored wire that is specifically designed to meet JIS Grade AA requirements, with halide content <1,000ppm, for no-clean lead-free applications. It offers the balance of high SIR reliability and excellent spread characteristics. It is among the best performing products in the ALPHA Cored Wire Product portfolio. Excellent soldering performance provides users with efficiency gains from higher first pass yields and faster soldering.

ALPHA Telecore XL-825 fast wetting and low spattering characteristics make it excellent for manual assembly and “drag soldering” technique. It is safe to use and operator friendly. Inspection is also made easier by its clear residue.

FEATURES & BENEFITS

- *Very fast wetting* → *Excellent for “Drag Solder” Technique. High Throughput.*
- *Very low flux spatter* → *Safe to use, Operator Friendly Less Residues on Boards.*
- *Good spread characteristics* → *Excellent First Pass Solder Joints, conferring high throughput. JIS Spread ≥ 80%.*
- *Very low levels of fumes* → *Cleaner Working Environment. Less Extraction Maintenance.*
- *Vanilla scented* → *Users experience improved comfort levels of fumes odour.*
- *Clear non-tacky residue* → *No-Clean Residues. Useful for all Applications.*
- *Provides good joint appearance* → *Makes Inspection easy.*

ALPHA Telecore XL-825 is suitable for use in any commercial no-clean hand soldering application that specifies compliance to JIS grade AA standard.

It is suited to such areas of industry (subject to the above criteria) as TV, Audio equipment, Video/DVD, Gaming Consoles, Automotive, Computer and peripherals, mobile and hand held devices and all types of household appliances. Flux content of 2.2% would be sufficient for most soldering applications as mentioned.

CONTINUED ON NEXT PAGE

ALPHA[®] TELECORE[™] XL-825

NO-CLEAN, WIRE SOLDER

PRODUCT INFORMATION

Standard	Alloy Designation	Melting or Solidus / Liquidus Temp °C	Flux Amount
J-STD-006B	SAC305	217 - 221	1.1%, 2.2% & 3.3%
Proprietary	SACX Plus 0807	217 - 228	2.2% & 3.3%
Proprietary	SACX Plus 0307	217 - 228	2.2% & 3.3%
Proprietary	SnCX Plus 07	227 - 229	2.2% & 3.3%
ISO 9453	Sn99.3/Cu0.7	227	2.2% & 3.3%
ISO 9453	Sn40/Pb60	183 - 238	2.2%
ISO 9453	Sn60/Pb40	183 - 190	2.2%
J-STD-006B	Sn63/Pb37	183	1.1%, 2.2% & 3.3%
ISO 9453	Sn60/Pb38/Cu2	183 - 191	1.1% & 2.2%

** ALPHA Telecore XL-825 may also be available in other alloys and flux amounts on request.*

APPLICATION

A soldered joint is formed by heating the parts to be soldered to a temperature in excess of the melting point of the alloy to be used – in hand soldering this is how a soldering iron is used. By feeding the cored wire onto the parts, the flux is able to flow and remove oxidized metal, while the solder creates a thin inter-metallic bond which becomes the solder joint. **ALPHA Telecore XL-825** is also ideal for robotic soldering applications.

Note the following tips:

- Use a soldering iron tip size and form to suit the operation: small tips for soldering large components may prevent the formation of a joint or slow the process down.
- Select a solder wire diameter to suit both the soldering iron tip and the parts/components to be soldered.
- Soldering iron systems should provide sufficient heat to satisfy the requirements of the points above.
- A typical solder tip temperature would be between 120°C and 160°C above the liquidus temperature of the alloy. The ideal temperature to use is dependent on how thermally demanding the assembly is.
- Cored solder wires can be provided in different grades of alloy so always ensure that you have selected the right grade for the application.
- Do not overheat as this causes an increase in the depth of the inter-metallic layer, which in turn weakens the joint.

ALPHA® TELECORE™ XL-825

NO-CLEAN, WIRE SOLDER

TECHNICAL DATA

Physical Properties	Typical Values
Rosin Softening Point:	70-80°C
Acid Value:	160-180 mg KOH/g flux
Halide Content:	< 1,000ppm per JIS Z 3197
Classification:	JIS - 1a3N Grade AA ROL1 per IPC J-STD-004A/B

Electrical Reliability Test	Requirements	Results
Automotive Damp-Heat Cyclic Test (IEC 60068-2-78)	$1.0 \times 10^8 \Omega$ minimum *	PASS
JIS SIR Test (JIS-Z-3197)	$1.0 \times 10^{11} \Omega$ minimum	PASS
JIS WER Test (JIS Z 3283:2006)	WER Class AA >1000 ohm-m	PASS
IPC SIR Testing (J-STD-004B)	$1.0 \times 10^8 \Omega$ minimum	PASS
Bellcore SIR Test (GR-78-CORE)	$1.0 \times 10^{11} \Omega$ minimum	PASS
Bellcore EM Test (GR-78-CORE)	SIR(initial)/SIR (Final) < 10	PASS

* IEC 60068-2-78 does not specify a minimum resistance value. Alpha has adopted the stated value.

Chemical Reliability Test	Requirements	Results
Copper Mirror Test JIS	No complete removal of copper	PASS
Copper Mirror Test IPC-TM 650 TM 2.3.32	No complete removal of copper	PASS
Copper Corrosion Test JIS	No evidence of corrosion	PASS
Copper Corrosion Test IPC-TM 650 TM 2.6.15	No evidence of corrosion	PASS

ALPHA® TELECORE™ XL-825

NO-CLEAN, WIRE SOLDER

SAFETY

Observe standard precautions for handling and use. Use in well ventilated areas. **DO NOT SMOKE.** ALPHA Telecore XL-825 wire is not considered toxic. However, its use in typical soldering applications will generate a small amount of decomposition and fumes. These fumes should be adequately exhausted / vented for operator safety and comfort.

Consult the SDS for all safety information. The most recent version of the SDS is available from alphaassembly.com.

STORAGE

ALPHA Cored Solder Wires should be stored in dry conditions and within a temperature range of 0°C to 40°C. When stored under these conditions the product shelf life is indefinite. However, Alpha guarantees the product shelf life for three years from the date of manufacture when stored in dry conditions and within 0°C to 40°C.

CONTACT INFORMATION

To confirm this is the most recent issue, please contact Alpha Assembly Solutions

AlphaAssembly.com

<p>North America 300 Atrium Drive Somerset, NJ 08873, USA 800.367.5460</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 01483.758400</p>	<p>Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
---	---	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency directory assistance Chemtrec 1 - 800 - 424 - 9300.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© Registered Trademark of MacDermid Performance Solutions. ™ Trademark of MacDermid Performance Solutions.
© Platform Specialty Products Corporation and its subsidiaries 2016.



Ihr Vertriebspartner/ Votre représentant:

Hilpert electronics AG
Täferstrasse 29
5405 Baden-Dättwil
Schweiz / Suisse

Tel: +41 56 483 25 25
Fax: +41 56 483 25 20
Mail: office@hilpert.ch
Web: www.hilpert.ch